1



## SAM™ Data Sheet SAM-1030-32-3ps-x, λ = 1030 nm


Laser wavelength		$\lambda = 1030 \text{ nm}$				
High reflection	band (R > 50%)	λ = 960 1050 nm				
Absorbance		A <sub>0</sub> = 32 %				
Modulation depth		ΔR = 20 %				
Non-saturable loss		A <sub>ns</sub> = 12 %				
Saturation fluence		$\Phi_{sat}$ = 60 µJ/cm <sup>2</sup>				
Relaxation time constant		τ ~ 3 ps				
Damage threshold		$\Phi = 800 \ \mu \text{J/cm}^2$				
Chip area		4mm x 4mm; other dimensions on request				
Chip thickness		450 μm;				
Protection		the SAM is protected with a dielectric front layer				
Mounting option x denotes the type of mounting as follows:						
	<b>x</b> = 0	unmounted				
	<b>x</b> = 12.7 g	glued on a gold plated Cu-cylinder with 12.7 mm $arnothing$				
	x = 25.4 g	glued on a gold plated Cu-cylinder with 25.4 mm $\varnothing$				

0	0	0 1	5
<b>x</b> = 12.7 s	soldered	on a gold plated	I Cu-cylinder with 12.7 mm $\emptyset$

x = 25.4 s soldered on a gold plated Cu-cylinder with 25.4 mm  $\varnothing$ 

x = FC	mounted on a 1	m	monomode	fiber	cable with	FC connector

## Low intensity spectral reflectance



BATOP GmbH Wildenbruchstraße 15 D-07745 Jena Germany Tel: +49 3641 634009 - 0 Fax: +49 3641 634009 - 20 E -mail: info@ batop.de 
 Deutsche Bank Erfurt
 VAT Reg.No: DE813698804

 Bank Code: 82070024
 Tax Acc. No: 162/106/01639

 Account No: 3922655
 Local Court Jena HRB 112769

 IBAN: DE49 8207 0024 0392 2655 00
 Local Court Jena HRB 112769