

SAM™ Data Sheet SAM-1550-15-12ps-x, $\lambda = 1550 \text{ nm}$

| | |
|--------------------------|--|
| Laser wavelength | $\lambda = 1550 \text{ nm}$ |
| High reflection band | $\lambda = 1450 \dots 1570 \text{ nm}$ |
| Absorbance | $A_0 = 15 \%$ |
| Modulation depth | $\Delta R = 8 \%$ |
| Non-saturable loss | $A_{ns} = 7 \%$ |
| Saturation fluence | $\Phi_{sat} = 70 \mu\text{J}/\text{cm}^2$ |
| Relaxation time constant | $\tau = 12 \text{ ps}$ |
| Damage threshold | $\Phi = 800 \mu\text{J}/\text{cm}^2$ |
| Chip area | 4.0 mm x 4.0 mm; other dimensions on request |
| Chip thickness | 450 μm |
| Protection | the SAM is protected with a dielectric front layer |

Mounting option **x** denotes the type of mounting as follows:

| | |
|-------------------|---|
| x = 0 | unmounted |
| x = 12.7 g | glued on a gold plated Cu-cylinder with 12.7 mm \varnothing |
| x = 25.4 g | glued on a gold plated Cu-cylinder with 25.4 mm \varnothing |
| x = 12.7 s | soldered on a gold plated Cu-cylinder with 12.7 mm \varnothing |
| x = 25.4 s | soldered on a gold plated Cu-cylinder with 25.4 mm \varnothing |
| x = 25.0 w | soldered on a water cooled Cu-cylinder with 25.0 mm \varnothing |
| x = FC | mounted on a 1 m single mode fiber cable with FC connector |

Low intensity spectral reflectance

