

HIGH TEMPERATURE ACRYLATE COATED SM FIBER



Fibercore's high temperature acrylate coated Single-Mode (SM) fibers are designed for continuous use at +150°C. The fibers are available with different Numerical Aperture (NA) ranges to give various levels of macro and micro bend losses and Mode Field Diameters (MFDs) to give the optimum choice depending upon the application.

The SM1500(9/125)HT is primarily designed as a low attenuation fiber for use as a transmission fiber or as a distributed sensor for Distributed Temperature Sensing (DTS), Distributed Pressure Sensing (DPS), Distributed Strain Sensing (DSS) and Distributed Acoustic Sensing (DAS) applications. The higher cut-off wavelength than standard telecoms fibers allows this fiber to offer improved bend losses over standard single-mode fibers.

The 6.4µm and 7.8µm MFD variants are designed to give very low macro and micro bend losses, higher backscattering coefficients for Raman, Rayleigh and Brillouin sensor systems and better splice compatibility to high NA, small MFD sensor coil fibers to allow use as a "bridging fiber" often used in acoustic sensors.

FEATURES

Advantages

- Engineered for high temperature applications up to +150°C
- Easy to strip high temperature acrylate coating
- High NA variants for extremely low macro and micro bend losses
- Reduced cladding options for high reliability coils and reduced package volume

Typical Applications:

- Geophones
- DTS, DAS, DSS and DPS
- Embedded Sensors
- Fiber Bragg Gratings (FBGs)
- Temperature Sensors

Product Variants

- SM1250(10.4/125)HT
10.4 core and 125 cladding for high temperature environments
- SM1500(5.3/80)HT
Bend insensitive fiber for high temperature environments
- SM1500(6.4/80)HT
Reduced diameter, bend insensitive fiber for tightly coiled applications in temperatures up to +150°C
- SM1500(6.4/125)HT
Bend insensitive fiber for distributed sensors in high temperature environments
- SM1500(7.8/125)HT
Bridging fiber to reduce splice losses between high temperature bend insensitive fibers and telecoms fibers
- SM1500(9/125)HT
Telecoms style, low attenuation, large MFD fiber with specialty high temperature acrylate coating

To find out more visit [fibercore.com](https://www.fibercore.com)

22July2020_MD01/8

HIGH TEMPERATURE ACRYLATE COATED SM FIBER

SPECIFICATIONS

	SM1250 (10.4/125)	SM1500 (5.3/80)HT	SM1500 (6.4/80)HT	SM1500 (6.4/125)HT	SM1500 (7.8/125)HT	SM1500 (9/125)HT
Operating Wavelength (nm)	1260 - 1650	1520 - 1650				
Cut-Off Wavelength (nm)	1190 - 1290	1350 - 1520				1300 - 1520
Numerical Aperture	0.11 - 0.14	0.23 - 0.24	0.19 - 0.21		0.15 - 0.17	0.13 - 0.15
Mode Field Diameter (μm)	9.6 - 11.2 @1250nm	5.0 - 5.6 @1550nm	6.0 - 6.8 @1550nm		7.3 - 8.3 @1550nm	8.5 - 9.9 @1550nm
Attenuation (dB/km)	≤0.24 @1550nm ≤0.38 @1310nm	≤0.8 @1550nm	≤0.5 @1550nm		≤0.4 @1550nm	≤0.35 @1550nm
Proof Test (%)	1 or 2 (100 or 200 kpsi)	1, 2 or 3 (100, 200 or 300 kpsi)				
Cladding Diameter (μm)	125 ± 1	80 ± 1		125 ± 1		
Core Cladding Concentricity (μm)	<1.0					
Coating Diameter (μm)	245 ± 15	≤0.5			≤0.75	≤0.4
Coating Type	High Temperature Acrylate					
Operating Temperature (°C)	-55 to +150					

RELATED PRODUCTS

- SM Fiber for Visible RGB Through to Near IR (SM)
- Polyimide Coated SM Fiber (SM-P)
- Pure Silica Core SM Fiber (SM-SC)
- Photosensitive Fibers (PS)

Fibercore House | Southampton Science Park
 United Kingdom | SO16 7QQ
 T +44 (0)23 8076 9893 | E info@fibercore.com

fibercore.com