


PURE SILICA CORE SM FIBER



Fibercore's Pure Silica Core SM fibers (SM-SC) are designed for high performance in demanding applications.

The SM1250SC(9/125) and SM1500SC variants are designed for use in hydrogen-rich environments where the pure silica core resists the effects of hydrogen darkening. The SM300-SC and SM400-SC are designed for Ultra-Violet (UV) and visible wavelength transmission. The silica core prevents photodarkening effects, which are normally associated with germanium doped fibers.

Fluorinated, depressed cladding design (see the image to the right) allows the core to be made from pure silica without the need for germanium doping.



FEATURES

Advantages

- Reduced hydrogen darkening
- Reduced UV induced photodarkening
- Polyimide variant
- Radiation tolerant core design
- Low attenuation 1550nm variants for long length sensors and communication

Typical Applications:

- Oil & Gas distributed sensors
- Biomedical illumination
- Microscopy
- Sensing in radiation and hydrogen environments
- Low attenuation telecoms transmission

Product Variants

- SM300-SC
Pure silica core fiber for transmitting long UV (UV-A) wavelengths without photodarkening
- SM400-SC
Non-photodarkening fiber for transmission of violet, blue and green wavelengths
- SM1250SC(9/125)
Very low attenuation, pure silica core fiber for 1550nm transmission
- SM1500SC(7/80)
Pure silica core, bend insensitive fiber
- SM1500SC(7/125)
Pure silica core, bend insensitive fiber

To find out more visit [fibercore.com](https://www.fibercore.com)

22July2020_MD23/8

SPECIFICATIONS

	SM300-SC	SM400-SC	SM1250SC (9/125)*	SM1500SC (7/80)	SSM1500SC (7/125)
Operating Wavelength (nm)	320 - 430	405 - 532	1260 - 1650	1520 - 1650	
Cut-Off Wavelength (nm)					
Dual Layer Acrylate (DLA)	≤310	≤400	1190 - 1290	1400 - 1500	
Polyimide (P)	-	-	1190 - 1290	1350 - 1520	
Numerical Aperture	0.12 - 0.14		0.13 - 0.15	0.17 - 0.19	
Mode Field Diameter (μm)	2.0 - 2.4 @350nm	2.7 - 3.3 @480nm	8.3 - 9.6 @1550nm	6.7 - 7.6 @1550nm	
Attenuation (dB/km)					
Dual Layer Acrylate (DLA)	≤70 @350nm	≤50 @430nm ≤30 @532nm	≤0.6@1310nm ≤0.4@1550nm	≤0.4@1550nm	≤0.7 @1550nm
Carbon High Temperature (CHT)	-	-	≤0.6@1310nm ≤0.4@1550nm	-	≤0.7 @1550nm
Polyimide (P)	-	-	≤0.8@1310nm ≤0.8@1550nm	≤0.75@1550nm	≤0.7 @1550nm
Carbon Polyimide (CP)	-	-	≤0.8@1310nm ≤0.8@1550nm	-	≤0.7 @1550nm
Proof Test (%)	1 or 2 (100 or 200 kpsi)				
Cladding Diameter (μm)	125 ± 1		125 ± 2	80 ± 1	125 ± 2
Core Cladding Concentricity (μm)	≤0.75				
Coating Diameter (μm)					
Dual Layer Acrylate (DLA)	245 ± 7		245 ± 15	170 ± 5	245 ± 7
Carbon High Temperature (CHT)	-	-	245 ± 15	-	245 ± 15
Polyimide (P)	-	-	155 ± 5	105 ± 5	155 ± 5
Carbon Polyimide (CP)	-	-	155 ± 5	-	155 ± 5
Coating Type	DLA	DLA, CHT, P* & CP	DLA & P	Polyimide	DLA, CHT, P & CP
Operating Temperature (°C)					
Dual Layer Acrylate (DLA)	-55 to +85				
Carbon High Temperature (CHT)	-	-	-55 to +150	-	-55 to +150
Polyimide (P)	-	-	-55 to +300		
Carbon Polyimide (CP)	-	-	-55 to +300	-	-55 to +300

* Special polyimide, for strip and recoat FBGs, available.

PURE SILICA CORE SM FIBER

RELATED PRODUCTS

- SM Fiber for Visible RGB Through to Near IR
- Polyimide Coated SM Fiber
- High Temperature Acrylate Coated SM Fiber
- Coreless End Cap Fiber

Fibercore House | Southampton Science Park
United Kingdom | SO16 7QQ
T +44 (0)23 8076 9893 | E info@fibercore.com

fibercore.com